

SPECIFICATION DATA



1. Product Name

Foam it Green® Foam it 12, 102, 202 and 602 Class I Disposable Foam Kits

2. Manufacturer

A&B Filling, Inc.
 PO Box 510803 | New Berlin, WI 53151
 Phone: 1-833-362-6484 Fax: 1-833-362-6484
 Email: sales@foamitgreen.com
 Web: www.foamitgreen.com

3. Product Description

Foam it Green® Foam it 12 Class I, 102 Class I, 202 Class I, and 602 Class I are disposable, closed-cell, low-pressure spray foam kits consisting of two chemical components (Component A: isocyanate and Component B: polyol blend), patented U-Control dispensing gun, two multi-purpose mixing nozzles (System 12) or ten multi-purpose mixing nozzles (Systems 102, 202 and 602), nitrile gloves, and packet of petroleum jelly. These systems contain a flame retardant formula, meeting requirements of ASTM E-84 as a Class I product. They do not require any external power source.

4. Technical Data

Foam it Green® Foam it 12, 102, 202 and 602 Class I have the following physical properties:

DENSITY (ASTM D1622):

Free Rise	1.75 lb/f ³
In Place	2.0 lb/f ³

R FACTOR at 1" thickness (ASTM C518): 6.7

COMPRESSIVE STRENGTH (ASTM D1621): 15.9 psi (parallel)

WATER ABSORPTION (ASTM D2842):
 % Volume Change / Lbs/Ft² 2.96% / 0.46

CLOSED CELL CONTENT (ASTM D2856): >95%

DIMENSIONAL STABILITY (ASTM D2842):
 % Volume Change, 158°F, 100 RH, 7 days 3.13
 % Volume Change, -80°F, 7 days -0.29

DIMENSIONAL STABILITY (ASTM D2126):
 % Volume Change, 158°F, 100 RH, 7 days 2.01
 % Volume Change, -60°F, 7 days -0.42

TEMPERATURE TOLERANCE:
 High Temperature Tolerance 250° F
 Low Temperature Tolerance -250° F

AIR BARRIER PROPERTIES at 75 Pa (ASTM E283): 0.005 L/s/m²

PERM RATING at 1" / at 3" (ASTM E96): 3.70 Perms / 1.83 Perms

TENSILE STRENGTH (ASTM D1623): 36.14 psi

FLAMESPREAD at 2" thickness (ASTM E84): 20

SMOKE DEVELOPED at 2" thickness (ASTM E84): 300

FUNGI RESITANCE (ASTM G21) No Growth

TACK FREE TIME: 30-40 seconds

RISE TIME: 30-40 seconds

YIELD:

System 12 Class I	1 f ³ 12 f ² @ 1" thick
System 102 Class I	9 f ³ 108 f ² @ 1" thick
System 202 Class I	16.5 f ³ 200 f ² @ 1" thick
System 602 Class I	50 f ³ 600 f ² @ 1" thick

- Foam it Green® products do not contain any CFC's, Penta-BDE's, VOC's, or Urea-Formaldehyde.
- Published yields are theoretical and vary based on several factors, including ambient conditions and specific application.
- Always use recommended personal protective equipment when using polyurethane foam products. Refer to the Material Safety Data Sheet for additional information on safe use and handling of Foam it Green® Systems.



5. Code Compliances

Foam it Green® Class I systems comply with the following codes:

- National Fire Protection Association – per NFPA 286 testing, cured product can be left exposed in a non-fire-resistant-rated roof/wall juncture, when applied at a maximum 6" high and 2" deep (unlimited width).